

PRODUCT DESCRIPTION

Generic: Waterborne Acrylic Epoxy

General Description: A professional grade, two package, chemically cured, waterborne acrylic epoxy coating combining performance properties of an epoxy and the color and gloss retention of an acrylic. May be used as a non-yellowing, durable high performance architectural coating (HIPAC). Suitable for use over aged conventional alkyd or latex finishes where more durability is desired. Also acceptable for use in exterior areas.

Typical Uses: Use on interior properly prepared poured concrete, concrete block, drywall, metal and wood. Ideal for hard usage areas of schools, hospitals, restaurants, public buildings and factories.

SPECIFICATION DATA

Color: White, tint base (0110)

Finish: 75 units minimum @ 60°

Clean-up Solvent: Soap and water

Weight/Gallon (mixed): 10.1 lbs./gal. (1.20 kg/L)

VOC (mixed): 2.03 lbs./gal. (244 g/L)

Solids By Volume (mixed): 40%± 2%

Theoretical Coverage at 1.0 Mil Dry: 642 sq. ft./gal. (15.8 m²/L)

Practical Coverage: Apply at 257-321 sq. ft./gal. (6.3- 7.9 m²/L) on smooth, sealed surfaces. Actual coverage may vary depending on substrate and application method.

Recommended Film Thickness: 2.0-2.5 mils (50-63 microns) dry - 5.0-6.3 mils (125-158 microns) wet

Systems: Please consult the appropriate system guide, the particular job specification or your ICI Paints Representative for proper systems using this product. Systems must be selected considering the particular environment involved.

Dry Time (ASTM D 1640): @ 77°F (25°C) & 50% RH

To touch - 1 hour

To recoat - 8 hours

Full Cure - 30 days

Ventilation, film thickness, humidity, thinning and other factors can influence the rate of dry.

Warning: The above table provides general guidelines only. Always consult your ICI Paints Representative for appropriate recoat windows since the maximum aged recoat time of this product may be significantly shortened or lengthened by a variety of conditions, including, but not limited to humidity, surface temperature, and the use of additives or thinners. The use of accelerators or force curing may shorten the aged recoat of individual coatings. The above recoat windows may not apply if recoating with a product other than those listed above. If the maximum aged recoat window is exceeded, please consult your ICI Paints Representative for appropriate recommendations to enhance adhesion. Failure to observe these precautions may result in intercoat delamination.

Shelf Life: 1 year minimum - unopened

Mix Ratio By Volume: 4 (base): 1 (converter)

Induction: None

Pot Life: 8 hours @ 77°F (25°C)

FEATURES

Advantages:

- Non-Yellowing
- Good gloss and color retention
- Low odor
- Low VOC
- Scrub resistant
- Stain resistant
- Interior/exterior

Limitations of Use: Not recommended for immersion service, floors or areas subject to constant high levels of moisture or direct application to new masonry surfaces.

PERFORMANCE DATA

PROPERTY	TEST METHOD	RESULTS
Abrasion Resistance	ASTM D 4060, CS-17 wheels, 1000g load, 1000 cycles	150mg loss
Pencil Hardness	ASTM D 3363	2B
Chemical/Stain Resistance (catsup, ball point pen, cola, lipstick, coffee, aliphatic hydrocarbons, water, dilute mineral and organic acids)	ASTM D 1308	Excellent resistance
Service Temperature Limit:		200°F (93°C) in air May discolor at temperatures over 140°F (60°C).
Flame Spread Rating:	ASTM E 84	Class A (0-25) over non-combustible surfaces

DANGER! FLAMMABLE. HARMFUL OR FATAL IF SWALLOWED. Read label and Material Safety Data Sheet Prior to Use. See other cautions on last page. DSF3-0696

GENERAL SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, form release agents, curing compounds, efflorescence, loose and flaking paint and other foreign substances.

New Surfaces: Concrete, Plaster and Masonry- Cure at least 30 days before painting. pH must be 10.0 or lower. Remove laitance and roughen unusually slick poured or pre-cast concrete by acid etching or abrasive sweeping. Follow acid manufacturer's application and safety instructions. Rinse thoroughly with water and allow to dry. Remove loose aggregate. Prime concrete with PREP & PRIME® GRIPPER® 3210 or DEVFLEX™ 4020 primer. Fill block with latex filler BLOXFIL® 4000 or PREP & PRIME® 3010 filler, then prime with waterborne primer PREP & PRIME GRIPPER 3210 or DEVFLEX 4020 primer. Fillers must dry overnight before coating. **Drywall** - Prime with PREP & PRIME GRIPPER 3210 primer. **Wood-** Prime with PREP & PRIME GRIPPER 3210 primer. **Steel** - Prime with TRU-GLAZE-WB™ 4030 epoxy primer. **Galvanized Metal and Aluminum-** Prime with TRU-GLAZE-WB 4030 epoxy primer. **Glazed Brick, Ceramic Tile and Fiberglass-** Scuff sand and prime with

TRU-GLAZE-WB 4030 epoxy primer.

Previously Painted Surfaces: The waterborne components of this product generally allow use over most old coatings. Old coatings should be tested for lifting. If they lift, remove them. Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Dull glossy areas by light sanding. Remove sanding dust. Remove loose paint. Prime bare areas with primer specified under **New Surfaces**.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

DIRECTIONS FOR USE

Tinting: Tint the appropriate 4418-0110 Component A base with ICI Paints Colorants. White is tintable up to 2 ozs./gal.

Mixing: Power mix while slowly adding 4418-9999 Component B to 4418-0110 Component A in a 1:4 ratio. Mix thoroughly and scrape sides of can to ensure thorough blending. Mixed material is usable for eight hours at 77°F (25°C), less at higher temperatures. If it thickens, discard and mix fresh material. Do not add flow-control materials. Avoid storing or placing containers in direct sunlight.

Spreading Rate: Apply at 257-321 sq. ft./gal. (6.3-7.9 m²/L) or 5.0-6.3 mils wet (2.0-2.5 mils dry) on smooth, sealed surfaces. Actual coverage may vary depending on substrate and application method. For best hiding, tint primers toward finish coat color. Certain shades of yellow, orange, pink and red may require multiple coats.

Application: May be applied by brush, roll or spray. Brushing and rolling may

require multiple coats to achieve correct film thickness and/or hiding. No thinning required. For airless spray, use a .015-.019" tip. Adjust pressure as needed. Spray is preferred for appearance and build. For roller application, use clean short nap roller (new rollers must be free of loose fibers). Brushing is best reserved for small areas of "cutting in". For maximum gloss development, two finish coats of this product are recommended. In some cases, one coat may be sufficient depending on the application method, color used and smoothness desired. Do not apply when surface or air temperature is below 50°F (10°C).

Drying Time (ASTM D 1640): At 77°F (25°C) and 50% R.H., dries to touch in one hour and to recoat in 8 hours. Full cure in 30 days. Low temperature, high humidity, thick films or poor ventilation will increase these times.

Clean-up: Clean immediately with warm, soapy water.

PRECAUTIONS

DANGER! FLAMMABLE LIQUID AND VAPOR. HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD - CAN ENTER LUNGS AND CAUSE DAMAGE. HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. OVEREXPOSURE MAY CAUSE KIDNEY DAMAGE. CONTAINS CRYSTALLINE SILICA WHICH CAN CAUSE LUNG CANCER AND OTHER LUNG DAMAGE IF INHALED. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. NOTICE: Products in this series contain solvents. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. For emergency information call (800) 545-2643. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.** Keep away from heat, sparks and flame. **Do not** smoke. Vapors may ignite. Extinguish all flames, burners, stoves, heaters and pilot lights and disconnect all electrical motors and appliances before use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. If sanding is done, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** In case of skin contact, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. For eye contact, flush immediately with large amounts of water, for at least 15 minutes. **Obtain emergency medical treatment.** If swallowed, **obtain medical treatment immediately.** If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help. **KEEP FROM FREEZING.**

DS198-1003

SHIPPING

Flash Point: None
Packaging: 1 gallon kit (3.785L) 5 gallon kit (18.925L)
 1 gallon Component A 4 gallons Component A
 1 quart Comp. B or C 1 gallon Component B

Shipping Weight: 1 gallon kit - 12 lbs. (5.4 kg)
 5 gallon kit - 57 lbs. (25.9 kg)

4418 (05/07)
 Ad Stock #68623C



Strongsville, Ohio U.S.A.
 800-654-2616
www.devoecoatings.com

LIMITATION OF LIABILITY: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained therein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.